

CAPITOL RECTIFIED PORCELAIN

Technical Specifications

Test	Standard Requirements	Test Results
Water Absorption UNI EN ISO 10545-03	Bla (GL) <=0.5%	<0.5%
Breaking Strength UNI EN ISO 10545-04	Minimum: 1300 N	>1600 N
Modulus of Rupture UNI EN ISO 10545-04	Minimum: 35 N/mm ²	>35 N/mm ²
Shock Resistance UNI EN ISO 10545-05	Suggested Minimum: E>0.55	Resistant
Resistance to Deep Abrasion UNI EN ISO 10545-06	Maximum: 175 mm ³	N/A
Linear Thermal Expansion UNI EN ISO 10545-08	As Reported	< 7.0 × 10 ⁻⁶ / °C
Thermal Shock Resistance UNI EN ISO 10545-09	Required	Resistant
Moisture Expansion UNI EN ISO 10545-10	As Reported	0.1 mm/m
Frost Resistance UNI EN ISO 10545-12	Required	Resistant
Chemical Resistance UNI EN ISO 10545-13	Domestic Chemical Products: GB / Acids and Alkalis: As reported	Complies with the standard
Stain Resistance UNI EN ISO 10545-14	Minimum: Class 3	Class 3
PEI Rating (Scratch Resistance) ASTM C 1027	As Reported	IV
Dynamic Coefficient of Friction (DCOF) ANSI A137.1	For Level Interior Spaces Expected to be walked upon when wet >0.42	> 0.42
Shade Variation	-	V2
Thickness	-	12" x 24" - 9.5 mm 24" x 24" - 9.5 mm 24" x 48" - 9 mm 40" x 40" - 9mm 48"x48" - 10.2 mm
Number of Screens	-	12" x 24" - 56 24" x 24" - 28 24" x 48" - 14 40" x 40" - 7 48" x 48"-7

B O L D  **SURFACES**
— BEST OF LUXURY DESIGN —